

## PELLETS RANGE

| POLYMER-BOUND<br>MIXLAND+<br>PELLETS |   | CHEMICAL NAMES  | ACTIVE<br>CONTENT<br>(%) | FILTRATION<br>(microns) | COLOUR           | ML (1+4)<br>at 50°C<br>(typical values) |
|--------------------------------------|---|---|--------------------------|-------------------------|------------------|---|
| AZTF 75 GE (*)                       | ② | Azodicarbonamide  | 75                       | -                       | Light orange     | 35                                      |
| CBS 80 GA F140                       | ① | N-cyclohexyl-2-benzothiazyl sulfenamide                 | 80                       | 140                     | Blue             | 30                                      |
| CTPI 80 GA F500                      | ① | N-cyclohexylthiophthalimide                             | 80                       | 500                     | Off white        | 50                                      |
| DOTG 75 GA F140                      | ② | Diorthotolyl guanidine                                  | 75                       | 140                     | Dark grey        | 35                                      |
| DPG 80 GA F140                       | ② | Diphenyl guanidine                                      | 80                       | 140                     | Mauve            | 40                                      |
| DPTT 75 GA F140                      | ① | Dipentamethylenethiuram hexasulfide                     | 75                       | 140                     | Beige            | 30                                      |
| DTDM 80 GA F200                      | ① | 4,4' -Dithiodimorpholine                                | 80                       | 200                     | White to Beige   | 30                                      |
| ETU 80 GA F140                       | ① | Ethylene thiourea                                       | 80                       | 140                     | White            | 35                                      |
| ETU 80 GA F500                       | ① | Ethylene thiourea                                       | 80                       | 500                     | White            | 35                                      |
| HMT 80 GA F500                       | ① | Hexamethylenetetramine                                  | 80                       | 500                     | White            | 40                                      |
| MBT 80 GA F140                       | ① | 2-Mercaptobenzothiazole                                 | 80                       | 140                     | Light brown      | 25                                      |
| MBTS 75 GA F140                      | ① | 2,2' -Dibenzothiazole disulfide                         | 75                       | 140                     | Light green      | 40                                      |
| MMBI 70 GA F200                      | ① | Methyl-2-mercaptobenzimidazole                          | 70                       | 200                     | Beige            | 35                                      |
| NDBC 75 GA F200                      | ① | Nickel dibutyl dithiocarbamate                          | 75                       | 200                     | Dark green       | 40                                      |
| OTOS 75 GA F200                      | ① | N-oxydiethylenethiocarbamyl-N-oxydiethylenesulfenamide  | 75                       | 200                     | White to greyish | 35                                      |
| PBS-R 80 GA F500                     | ① | N-Phenyl-N (Trichloromethylsulfenyl)-benzenesulfonamide | 80                       | 500                     | Pale pink        | 30                                      |
| S 80 GA F500                         | ① | Sulphur   | 80                       | 500                     | Yellow           | 30                                      |
| S M300 80 GA F140                    | ① | Sulphur   | 80                       | 140                     | Yellow           | 35                                      |
| TBBS 75 GA F200                      | ① | N-ter.-butyl-2-benzothiazolesulphenamide                | 75                       | 200                     | Beige            | 32                                      |
| TBP 75 GA F100                       | ② | Poly-Tert-Butylphenoldisulfide                          | 75                       | 100                     | Beige            | 40**                                    |
| TBzTD 70 GA F140                     | ① | Tetrabenzyl thiuram disulfide                           | 70                       | 140                     | Beige            | 50                                      |
| TDEC 75 GA F140                      | ① | Tellurium diethyldithiocarbamate                        | 75                       | 140                     | Orange           | 40                                      |
| TMTD 80 GA F140                      | ① | Tetramethylthiuram disulfide                            | 80                       | 140                     | Light orange     | 30                                      |
| TMTM 80 GA F500                      | ① | Tetramethylthiuram monosulfide                          | 80                       | 500                     | Yellow           | 40                                      |
| TTC-R 80 GA F140 (*)                 | ① | Tetrahydro-N-(trichloromethylthio)phthalimide           | 80                       | 140                     | Beige            | 35                                      |
| ZBEC 70 GA F100                      | ① | Zinc dibenzyl dithiocarbamate                           | 70                       | 100                     | White to greyish | 30                                      |
| ZDBC 80 GA F140                      | ① | Zinc dibutyl dithiocarbamate                            | 80                       | 140                     | White to greyish | 30                                      |
| ZDEC 75 GA F140                      | ① | Zinc diethyl dithiocarbamate                            | 75                       | 140                     | White to greyish | 40                                      |
| ZDMC 75 GE F500 (*)                  | ② | Zinc dimethyl dithiocarbamate                           | 75                       | 500                     | White to Beige   | 40                                      |
| ZDTP 50 GA F500                      | ① | Zinc dialkyl dithiophosphate                            | 50                       | 500                     | Beige to greyish | 63                                      |
| ZEPC 80 GA F140                      | ① | Zinc ethyl phenyl dithiocarbamate                       | 80                       | 140                     | White            | 35                                      |
| ZNO 90 GA F140 (*)                   | ② | Zinc oxide  | 90                       | 140                     | Yellowish        | 40                                      |
| ZNO 90 GA F500 (*)                   | ② | Zinc oxide  | 90                       | 500                     | Yellowish        | 40                                      |

## SLABS RANGE

| POLYMER-BOUND<br>MIXLAND+<br>SLABS |   | CHEMICAL NAMES                             | ACTIVE<br>CONTENT<br>(%) | FILTRATION<br>(microns) | COLOUR           | ML (1+4)<br>at 50°C<br>(typical values) |
|------------------------------------|---|--|--------------------------|-------------------------|------------------|---|
| AZTF 75 BE (*)                     | ② | Azodicarbonamide                           | 75                       | -                       | Khaki green      | 42.5                                    |
| CBS 75 BA F140                     | ② | N-cyclohexyl-2-benzothiazyl<br>sulfenamide | 75                       | 140                     | Blue             | 30                                      |
| DOTG 75 BA F140                    | ② | Diorthotolyl guanidine                     | 75                       | 140                     | Dark grey        | 35                                      |
| DPTT 75 BA F140                    | ② | Dipentamethylenethiuram hexasulfide        | 75                       | 140                     | Violet           | 35                                      |
| DTDM 75 BA F140                    | ② | 4',4'-Dithiodimorpholine                   | 75                       | 140                     | White to beige   | 35                                      |
| MBT 75 BA F140                     | ② | 2-Mercaptobenzothiazole                    | 75                       | 140                     | Light brown      | 35                                      |
| MBTS 75 BA F140                    | ② | 2,2'-Dibenzothiazole disulfide             | 75                       | 140                     | Light green      | 35                                      |
| S M300 75 BA F140                  | ② | Sulphur                                    | 75                       | 140                     | Yellow           | 35                                      |
| TMTD 80 BA F140                    | ② | Tetramethylthiuram disulfide               | 80                       | 140                     | Light orange     | 35                                      |
| ZBEC 75 BA F140                    | ② | Zinc dibenzyl dithiocarbamate              | 75                       | 140                     | White to greyish | 35                                      |
| ZDBC 80 BA F140                    | ② | Zinc dibutyl dithiocarbamate               | 80                       | 140                     | Light blue       | 40                                      |
| ZDEC 75 BA F140                    | ② | Zinc diethyl dithiocarbamate               | 75                       | 140                     | Light violet     | 35                                      |
| ZDTP 50 BA F500                    | ② | Zinc dialkyldithiophosphate                | 50                       | 500                     | Beige to greyish | 45                                      |

(\*) Available on request

**PACKAGING** ① 20 kg net PE bags, 640 kg net CP3 pallets (1140x1140)  
② 25 kg net cardboard, 600 kg net CP3 pallets (1140x1140)